

## **Chemical resistance guide for Jet**

It is important to note that the performance of these chemicals may be different if mixtures of chemicals are involved.

<b>Chemical</b>	<b>EN374 performance level</b>
1-Methoxy-2-propanol	3
Acetic acid (glacial)	4
Acetic anhydride	6
Acetone	1
Ethyl acetate	1
Formic acid 99%	3
Hydrochloric acid 32%	6
Isopropyl alcohol	5
Methanol	3
Nitric acid 70%	4
Oxalic acid (saturated solution)	6
Perchloroethylene	1
Phosphoric acid 85%	6
Sodium hydroxide 40%	5
Styrene	0
Sulphuric acid 50%	6
Sulphuric acid 96%	2
Tetrahydrofuran	0
Toluene	0
Xylene	1

### **EN374 Performance Levels**

<b>Performance Level</b>	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>	<b>5</b>	<b>6</b>
Breakthrough time (mins)	>10	>30	>60	>120	>240	>480

The information contained here is advisory and is intended to guide and inform only. This information is based on the view on BM Polyco Ltd in light of all available data and is not subject to any guarantee on our part regarding the performance of a particular glove style. As it is impossible to test every situation encountered and all chemical and mixtures of chemicals, the user is advised to test the particular glove style before and periodically during use.